

Chemical Resistance

Chemical Compatibility Table

CHEMICAL	SERIES P (POLY/GLASS) 70°–160°F		SERIES V (VINYL/GLASS) 70°–160°F		SERIES PU (POLYURETHANE) 70°–160°F	
	70°F	160°F	70°F	160°F	70°F	160°F
Acetic Acid, Up to 10%	R	R	R	R	R	–
Acetic Acid, Up to 50%	R	R	R	R	R	–
Acetone, Up to 10%	NR	NR	NR	NR	R	–
Aluminum Hydroxide	R	R	R	R	R	–
Ammonium Hydroxide (Aqueous Ammonia), Up to 5%	NR	NR	R	R	R	–
Ammonium Hydroxide, Up to 10%	NR	NR	R	150°	R	–
Ammonium Hydroxide, Up to 20%	NR	NR	R	150°	R	–
Ammonium Nitrate	R	R	R	R	R	–
Ammonium Phosphate	R	R	R	R	R	–
Ammonium Sulfide, Saturated	NR	NR	R	120°	R	–
Aqua Regia, fumes	NR	NR	R	150°	NR	–
Benzene NR	NR	NR	NR	NR	R	R
Benzoic Acid	R	R	R	R	R	–
Bromine, Wet Gas	NR	NR	R	150°	–	–
Butylene Glycol, Up to 100%	R	R	R	NR	R	–
Butyric Acid, Up to 50%	R	R	R	R	R	–
Calcium Hydroxide	R	NR	R	R	R	–
Calcium Hypochlorite	R	NR	R	R	R	–
Chlorine, Dry Gas	NR	NR	R	R	–	–
Chlorine, Wet Gas	NR	NR	R	R	–	–
Chlorine, Liquid	NR	NR	NR	NR	–	–
Chlorine, Water	R	R	R	R	R	–
Chromic Acid, Up to 5%	NR	NR	R	R	–	–
Copper Chloride	R	R	R	R	R	–
Copper Cyanide	R	NR	R	R	R	–
Copper Fluoride	R	NR	R	R	R	–
Copper Nitrate	R	R	R	R	R	–
Copper Sulfate	R	R	R	R	R	–
Dechlorinated Brine Storage	–	–	R	R	R	–
Esters, Fatty Acid	R	R	R	R	R	–
Ferric Chloride	R	R	R	R	R	–
Ferrous Chloride	R	R	R	R	R	–
Fluoboric Acid	R	120°	R	R	–	–
Fluosilicic Acid, Up to 10%	NR	NR	R	R	–	–
Fluosilicic Acid, Up to 32%	NR	NR	R	100°	–	–
Formic Acid, Up to 10%	NR	NR	R	R	R	–
Formic Acid, Up to 50%	NR	NR	R	100°	R	–
Gasoline, Aviation	R	NR	R	R	R	–
Green Liquor, Pulp Mill	–	–	R	R	–	–
Hydrochloric Acid, Up to 15%	R	NR	R	R	R	–

R = Recommended NR = Not recommended – = No information available



CHEMICAL	SERIES P (POLY/GLASS) 70°–160°F		SERIES V (VINYL/GLASS) 70°–160°F		SERIES PU (POLYURETHANE) 70°–160°F	
	70°F	160°F	70°F	160°F	70°F	160°F
Hydrochloric Acid, Up to 37%	R	NR	R	R	R	–
Hydrofluoric Acid, Up to 10%	NR	NR	R	150°	–	–
Hydrofluoric Acid, Up to 20%	NR	NR	R	100°	–	–
Hydrogen Chloride, Wet Gas	R	NR	R	R	NR	–
Hydrogen Sulfide, Wet Gas	R	NR	R	R	R	–
Lactic Acid	R	NR	R	R	R	–
Lead Nitrate	–	–	R	R	R	–
Magnesium Hydroxide	NR	NR	R	R	R	–
Nickel Sulfate, Low pH	NR	NR	R	R	R	–
Nickel Sulfate, High pH	NR	NR	R	R	R	–
Nitric Acid, Up to 5%	NR	NR	R	150°	R	–
Nitric Acid, Up to 35%	NR	NR	R	150°	R	–
Nitric Acid, Vapor	NR	NR	R	R	–	–
Perchloric Acid, Up to 10%	NR	NR	R	150°	–	–
Pickling Liquids, 3–5% H2SO4	R	R	R	R	R	–
Phosphoric Acid	NR	NR	R	R	R	–
Phosphoric Acid, Super or Poly (115%, P20%)	NR	NR	R	R	–	–
Phosphoric Acid, Vapor or Condensate	NR	NR	R	R	–	–
Potassium Chloride	R	R	R	R	R	–
Potassium Nitrate	R	R	R	R	R	–
Potassium Persulfate	NR	NR	R	R	R	–
Silver Cyanide, Up to 5%	NR	NR	R	R	R	–
Sodium Hydroxide, Up to 25%	NR	NR	R	150°	R	–
Sodium Hydroxide, Up to 50%	NR	NR	R	180°	–	–
Sodium Hypochlorite, Up to 15%	NR	NR	R	150°	R	–
Sodium Nitrate	R	R	R	R	R	–
Sodium Sulfate	R	NR	R	R	R	–
Sodium Sulfide	NR	NR	R	R	R	–
Sulfuric Acid, Up to 25%	R	R	R	R	R	–
Sulfuric Acid, Up to 50%	NR	NR	R	R	R	–
Sulfuric Acid, Up to 70%	NR	NR	R	R	R	–
Sulfuric Acid, Up to 75%	NR	NR	R	120°	–	–
Sulfuric Acid, Up to 80%	NR	NR	NR	NR	–	–
Sulfuric Acid, Vapor	R	NR	R	R	–	–
Trichlorethylene, Fumes	NR	NR	R	120°	R	–
Trisodium Phosphate	R	NR	R	R	R	–
Urea	R	NR	R	150°	R	–
Vegetable Oils	R	R	R	R	R	–
Vinegar	R	R	R	R	R	R
White Liquor, Pulp Mill	–	–	R	R	–	–

R = Recommended NR = Not recommended – = No information available

Note: The recommendations contained in this table (pages 9-10) are made without guarantee of representation as to results. Since the actual use by others is beyond our control, no guarantee, expressed or implied, is made by Champion Fiberglass as to effects of such use or results to be obtained nor does Champion Fiberglass assume any liability arising out of the use by others of the products referenced in this table (pages 9-10). Nor is the information herein to be construed as absolutely complete since additional information may be needed or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence, or otherwise is limited to the purchase price of the material.